

# Goldspar Satin : Varnishes

Interior Satin Finish on Timber

## PRODUCT DESCRIPTION

A satin finish polyurethane varnish designed primarily for interior use. Resistant to hot water, mild acids and alkalis. The quick drying formulation minimises dust contamination.

\* Fast dry to reduce dust pickup

## PRODUCT INFORMATION

<b>Colour</b>	YVA251
<b>Finish</b>	Satin
<b>Specific Gravity</b>	0.9
<b>Volume Solids</b>	46%
<b>Typical Shelf Life</b>	2 yrs
<b>VOC (As Supplied)</b>	425 g/lit
<b>Unit Size</b>	500 ml 1 Lt 2.5 Lt

## DRYING/OVERCOATING INFORMATION


	<b>Drying</b>							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Touch Dry [ISO]	5 hrs		3 hrs		1 hrs		30 mins	
	<b>Overcoating</b>							
	<b>Substrate Temperature</b>							
Overcoated By	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
	Min	Max	Min	Max	Min	Max	Min	Max
Goldspar Satin :	24 hrs	4 days	15 hrs	3 days	6 hrs	2 days	3 hrs	1 days


**Note:** If Maximum Recoat Times are exceeded, sand using 320-400 grade (grit) wet or dry paper.

## APPLICATION AND USE

<b>Preparation</b>	All surfaces to be coated should be clean, dry and free from contamination.
<b>Method</b>	Avoid using direct from the can. Pour the amount you expect to use in a separate container.
<b>Hints</b>	<p><b>Thinner</b> YTA800 International Enamel Thinners #1. Thin up to 30% as required when spraying.</p> <p><b>Cleaner</b> YTA800 International Enamel Thinners #1.</p> <p><b>Ventilation and Humidity Control</b> Ensure adequate ventilation during use.</p> <p><b>Airless Spray</b> Pressure: 176-210 bar. Tip Size: 1365-1580.</p> <p><b>Conventional Spray</b> Pressure: 2.3 bar. Tip Size: 1.1-1.4 mm.</p> <p><b>Other</b> For Airmix spray application: Pressure: 2.0 bar. Tip Size: 06-113. For a particularly clear finish use Goldspar gloss for the first 2 or 3 coats and Goldspar Satin : only for the final coat.</p>
<b>Some Important Points</b>	Product temperature should be minimum 15°C/59°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/41°F and maximum 35°C/95°F.
<b>Compatibility/Substrates</b>	Suitable for Timber above the Waterline. For interior use only. May be applied after thinning, to naturally oily timbers such as Teak and Iroko after suitable degreasing.
<b>Number of Coats</b>	2-3
<b>Coverage</b>	(Theoretical) - 11.5 m <sup>2</sup> /lt (Practical) - 10.3 m <sup>2</sup> /lt by brush, 9 m <sup>2</sup> /lt by spray
<b>Recommended DFT</b>	40 microns dry
<b>Recommended WFT</b>	87 microns wet
<b>Application Methods</b>	Airless Spray, Brush, Conventional Spray, Airmix, Roller

Please refer to your local representative or visit [www.yachtpaint.com](http://www.yachtpaint.com) for further information.

 International®, the AkzoNobel logo and other products mentioned in this publication are trademarks of, or licensed to Akzo Nobel. ©Akzo Nobel 2009.



# Goldspar Satin : Varnishes

Interior Satin Finish on Timber

---

## TRANSPORTATION, STORAGE AND SAFETY INFORMATION

### Storage

#### TRANSPORTATION:

Goldspar Satin : should be kept in securely closed containers during transport and storage.

#### STORAGE:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Goldspar Satin : to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.

### Safety

**DISPOSAL:** Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

**GENERAL:** Read the label safety section for Health and Safety Information, also available from our Technical Help Line. Always use gloves and goggles and keep skin protected with overalls. Users should ensure they have a copy of the Material Safety Datasheet for this product and that they are familiar with all the safety directions before use.

### IMPORTANT NOTES

*The technical information and suggestions for use and application presented herein are not intended to be exhaustive, but they represent the best information available to use and are believed to be reliable. They should not, however, be construed as controlling suggestions and there is no warranty of performance of our materials either expressed or implied. We urge that users of our materials conduct confirmatory tests to determine final suitability for their specific end uses. Because this datasheet is subject to changes from time to time, it is the user's responsibility to check that this sheet is current prior to using the product.*